

## SPECIFICATION SHEET

Commodity	:Polyester Chip Cation Dyeable	
Application	:Textile Grade, Flament Yarn	
Origin	:Korea	
PROPERTY	UNIT	RANGE
<i>Intrinsic viscosity</i>	DL/G	0.545 ± 0.02
<i>Color</i>	<i>b VALUE</i>	5.0 Max
	<i>L VALUE</i>	72 Min
<i>TiO2</i>	%	0,24 ± 0.02
<i>DEG</i>	meq/kg	6.0 Max
<i>Carboxyl End Group</i>	eq/ton	50 Max
<i>Melting point</i>	°C	240.0 ± 3.0
<i>Moisture</i>	wt%	0.20 MAX
<i>Chip Size</i>	pcs/g	42± 5
<i>Packing</i>	:1000KGS IN PP WOVEN JUMBO BAGS	
<i>Container Loading</i>	:20MT (20BAGS) IN 1 X 20FT CONTAINER	



### Copyright Tesport 2020

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Tesport F.T. cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Adnan Kahveci Mah.  
Sayaca Cad. Ekol Center  
Kat 2 No:50 Beylikduzu  
Istanbul - Turkey  
Tel: +90 212 856 05 01  
www.tesport.com  
resin@tesport.com